



TÜV SÜD America Inc.
Product Safety Services
 47253 Clipper Drive
 Plymouth, MI 48170
 Phone: 734.455.4841

IPEMA Surfacing Material Report – ASTM F1292-09

Client: International Mulch Products
 Manufacturer: International Mulch Products
 Manufacturing Location: Bridgeton, MO

TUV Report No.: QI1010083-8

Report Date: 12/13/2010

Test Date: 11/17/2010

Initial Test

Follow up Test Ref Job:

Sample Receipt Date: 11/16/2010

Selection Date: N/A

Ambient Air Temperature: 19.9°C

Humidity: 35%

Phone: 314.336.1030

Commercial Name of product: NuScape

Sample Selection: Yes: No: X

Date of Manufacture: Unknown

No. of samples submitted: 8 Cu. Ft.

Test Equipment:

Triax 2000 Accelerometer Calibration Due Date: Jan-11

Environmental Chamber No.: N/A

Temperature Probe Calibration Due Date: Jan-11

Calibration Due Date: N/A

Environmental Chamber No.: N/A

Calibration Due Date: N/A

Loose fill Material Sample Description:

- Loose Fill Wood:
- Engineered Wood Fiber:
- Rubber:
- Sand:
- Gravel:
- Other:

Un-compacted Depth: 3 Inches

Compacted Depth: 3 Inches

Unitary Sample Description:

- Tiles Thickness:
- Poured in Place Thickness:
- Other Thickness:

Comments:

The above described sample was tested at : 6 Ft.

The results reported herein reflect the performance of the above described samples at the time of testing and at the temperature(s) reported. The results are specific to the described samples. Samples of surfacing materials that do not closely match the described samples will perform differently. The following data sheet provides an accurate representation of the test results.

Sample in compliance with ASTM F1292-09 at the temperature and rating specified? Yes No

Signature: [Signature]

Date: 12/15/2010

Reviewed by: [Signature]

Date: 12/16/10

Client: **International Mulch Products**

TUV Report No. **QI1010083-8**

Manufacturer: **International Mulch Products**

Test Date: **11/17/2010**

Drop	Specified Drop Height (Ft.)	Reference Temperature -6°C, (21.2°F)			Reference Temperature 23°C,(73.4°F)			Reference Temperature 49°C,(120.2°F)		
		G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)
1	6				102	519	19.5			
2	6				105	503	19.5			
3	6				154	804	19.6			
Average		0	0		129.5	653.5		0	0	
Measured Surface Temperature		°C	Max. Change from reference + 5°C ,(9°F)		24°C	Max. Change from reference ± 3°C ,(5.4°F)		°C	Max. Change from reference -3°C ,(-5.4°F)	
Sample Condition:		DRY								

Drop	One foot over (Ft.)	Reference Temperature -6°C, (21.2°F)			Reference Temperature 23°C,(73.4°F)			Reference Temperature 49°C,(120.2°F)		
		G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)
1										
2										
3										
Average		0	0		0	0		0	0	
Measured Surface Temperature		°C	Max. Change from reference + 5°C ,(9°F)		°C	Max. Change from reference ± 3°C ,(5.4°F)		°C	Max. Change from reference -3°C ,(-5.4°F)	
Sample Condition:										

Drop	One foot under (Ft.)	Reference Temperature -6°C, (21.2°F)			Reference Temperature 23°C,(73.4°F)			Reference Temperature 49°C,(120.2°F)		
		G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)
1										
2										
3										
Average		0	0		0	0		0	0	
Measured Surface Temperature		°C	Max. Change from reference + 5°C ,(9°F)		°C	Max. Change from reference ± 3°C ,(5.4°F)		°C	Max. Change from reference -3°C ,(-5.4°F)	
Sample Condition:										



America