



TUV SUD America Inc.
 Product Safety Services
 47253 Clipper Drive
 Plymouth, MI 48170
 Phone: 734.455.4841

IPEMA Surfacing Material Report – ASTM F1292-09

Client: International Mulch Products
 Manufacturer: International Mulch Products
 Manufacturing Location: Bridgeton, MO

TUV Report No.: QI1010836-3
 Report Date: 12/22/2010
 Test Date: 12/21/2010
 Initial Test
 Follow up Test **Ref Job:**
 Sample Receipt Date: 10/20/2010
 Selection Date: N/A
 Ambient Air Temperature: 21.4
 Humidity: 35%

Phone: 314.336.1030
 Commercial Name of product: RePlay
 Sample Selection: **Yes:** No: X
 Date of Manufacture: Unknown
 No. of samples submitted: 12 Cu. Ft.

Test Equipment:

Triax 2000 Accelerometer Calibration Due Date: Jan-11
 Temperature Probe Calibration Due Date: Jan-11

Environmental Chamber No.: PLYP00101
 Calibration Due Date: 8/18/11
 Environmental Chamber No.: PLYP00069
 Calibration Due Date: 8/18/11

Loose fill Material Sample Description:

- Loose Fill Wood:
- Engineered Wood Fiber:
- Rubber:
- Sand:
- Gravel:
- Other:

Un-compacted Depth: 6 Inches
 Compacted Depth: 5.5 Inches

Unitary Sample Description:

- Tiles Thickness:
- Poured in Place Thickness:
- Other Thickness:

Comments:

The above described sample was tested at : 16 Ft.

The results reported herein reflect the performance of the above described samples at the time of testing and at the temperature(s) reported. The results are specific to the described samples. Samples of surfacing materials that do not closely match the described samples will perform differently. The following data sheet provides an accurate representation of the test results.

Sample in compliance with ASTM F1292-09 at the temperature and rating specified? Yes No

Signature: 

Date: 12/22/2010

Reviewed by: 

Date: 12/27/10

Client: International Mulch Products

TUV Report No. QI1010836-3

Manufacturer: International Mulch Products

Test Date: 12/21/2010

Drop	Specified Drop Height (Ft.)	Reference Temperature -6°C, (21.2°F)			Reference Temperature 23°C,(73.4°F)			Reference Temperature 49°C,(120.2°F)		
		G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)
1	16	105	720	31.8	113	795	31.8	105	690	31.8
2	16	102	634	31.7	117	805	31.7	101	608	31.7
3	16	99	611	31.7	148	1167	31.9	117	745	31.7
Average		100.5	622.5		132.5	986		109	676.5	
Measured Surface Temperature		(-4°C)	Max. Change from reference + 5°C ,(9°F)		21°C	Max. Change from reference ± 3°C ,(5.4°F)		48°C	Max. Change from reference -3°C ,(-5.4°F)	
Sample Condition:		DRY			DRY			DRY		

Drop	One foot over (Ft.)	Reference Temperature -6°C, (21.2°F)			Reference Temperature 23°C,(73.4°F)			Reference Temperature 49°C,(120.2°F)		
		G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)
1										
2										
3										
Average		0	0		0	0		0	0	
Measured Surface Temperature		°C	Max. Change from reference + 5°C ,(9°F)		°C	Max. Change from reference ± 3°C ,(5.4°F)		°C	Max. Change from reference -3°C ,(-5.4°F)	
Sample Condition:										

Drop	One foot under (Ft.)	Reference Temperature -6°C, (21.2°F)			Reference Temperature 23°C,(73.4°F)			Reference Temperature 49°C,(120.2°F)		
		G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)	G-Max	HIC	Velocity (ft/s)
1	N/A									
2										
3										
Average		0	0		0	0		0	0	
Measured Surface Temperature		°C	Max. Change from reference + 5°C ,(9°F)		°C	Max. Change from reference ± 3°C ,(5.4°F)		°C	Max. Change from reference -3°C ,(-5.4°F)	
Sample Condition:										

